



PRODUCT SPECIFICATIONS

MYLAR

PHYSICAL PROPERTIES

Product Weight: 21 oz. per lineal yd., (13oz. per sq. yd.)

Vinyl Weight: 16.5 oz. per lineal yd.

Polyester Weight: 1.5 oz. per lineal yd.

Fabric Weight: 3 oz. per lineal yd.

Thickness: 0.015 to 0.030 in.

*depending on texture

Fabric: Poly-Cotton Osnaburg or Polyester Nonwoven

*depending on texture

BREAKING STRENGTHS, LBS. FORCE

Machine Direction-warp:

*Exceeds Type II minimum of 50 lbs.

Cross Machine Direction-fill:

*Exceeds Type II minimum of 55 lbs.

TEARING STRENGTH, SCALE

Machine Direction-warp:

*Exceeds Type II minimum of 25lbs.

Cross Machine Direction-fill:

*Exceeds Type II minimum of 25 lbs.

FIRE TESTING

ASTM-E84 Tunnel Test Class A

*Meets or exceeds requirements for flame spread, smoke developments and flashover.

*Cadmium and Lead Free Formulation

